

ABIC TESTING LABORATORIES, INC.

24 Spielman Road
Fairfield, NJ 07004

973-227-7060
Fax: 973-227-0172

To: Devonian Stone of New York
Ms. Peggy Rosenthal

September 19, 2008

From: Leonard Mackowiak

Subject: Freeze –Thaw Resistance Testing, ASTM C-1026
Project No 5209-02

Introduction

ABIC Testing Laboratories, Inc. was authorized to test the following stone for freeze-thaw resistance according to ASTM C-1026.

- Glacier Blue Devonian Stone

Results

Sample Identification Freeze-Thaw Cycles (Stone Appearance)

	<u>5 cycles*</u>	<u>10 Cycles</u>	<u>15 Cycles</u>	<u>20Cycles</u>
Glacier Blue Devonian Stone	No effect	No Effect	No Effect	No Effect

* Previously soaked stone: One test cycle consists of 6-8 hours at 0°F followed by soaking 16 hours in water at room temperature

Discussion

The Glacier Blue Devonian Stone showed no change in appearance after twenty freeze-thaw cycles according to the test procedure in ASTM C-1026

Respectfully submitted,



Leonard Mackowiak
Vice President